

## ФАОЛЛАШТИРИЛГАН ҚУМЛИ ТҮЛДИРГИЧНИҢ ЦЕМЕНТХАМИРИВАЦЕМЕНТТОШ ИХОССАЛАРИГАТАСИРИ

Н.Тахиржанов

(Қарақалпоқ давлат университети стажёр ўқитувчisi)

Р.Айеэзбайев

(Қарақалпоқ давлат университети магистранти)

Е.Алланазаров

(Қарақалпоқ давлат университети магистранти)

**Аннотация:** Ушбу мақолада Фаоллаштирилган қумли түлдиргичнинг цемент хамири ва цемент тоши хоссаларига таъсири ўрганиб чиқилди.

**Калит сўзлар:** Бархан, мергел, цемент, ЛСТ, АЦФ, түлдиргичлар, дисперс.

Ҳозирги вақтда Ўзбекистоннинг чўлли районларида турли бинолар ва иншоотларнинг қурилиши кун сайин ривожланиб бормоқда. Бетон бу худудларида замонавий қурилишнинг асосий материали бўлиб қолмоқда. Бироқ Ўзбекистон Республикасининг бир қаторхудудларида бетон таркибига қўйиладиган талабларни қониқлантирувчи нормал йириклиқдаги қумнинг танқислиги кузатилмоқда ва майда донали қумдан, жумладан, бархан қумларидан фойдаланиш янада долзарб масала бўлиб қолмоқда.

Бархан қумлари асосидаги бетон қоришмаси ва бетон хоссаларини яхшилаш ҳамда цементнинг самарадор ва оддий технологик усулларини излаш ва тадқиқ қилиш Ўзбекистон шароитлари учун долзарб вазифалардан биридир.

Тўлдиргичлар, суюлтирувчи ва фаоллаштирувчи қўшимчалар цемент хамири ва цемент тошининг хоссаларига таъсир кўрсатади. Аввал бажарилган тадқиқотларни инобатга олиб,[1,2] ишда асосий эътибор цемент хамири ва тоши хоссалари ўзаришларининг табиатли моддалар билан фаоллаштирилган бархан қумидан олинган тўлдиргични киритишга миқдорий боғлиқлигини ўрнатишга қаратилди. Экспериментал тадқиқотларни олиб боришда этalon цемент сифатида оддий портландцементдан фойдаланилди. Нордон табиатли қўшимча (ЛСТ) цемент массасига нисбатан 0,15-0,6% ва АЦФ қўшимчаси 0,05-0,15% чегараларда, асосий табиатли қўшимча мергел эса қумли тўлдиргич массасига нисбатан 5-10% чегарасида қабул қилинди.

Одатда, тўлдиргичларнинг дисперслигини аниқлашда фақат минераль модда зарраларининг геометриясини ҳисобга олган ҳолда солиширма сирт-юзани ўрнатиш имконини берувчи методлардан фойдаланилди. [3,4] Дисперсли қаттиқ моддаларнинг зарралари ёриқлар ва бошқа дефектларга эга бўлиши мумкин, унда уларнинг фактли солиширма юзаси анча юқори бўлиши мумкин. Аввал бажарилган тадқиқотлар орқали қумли тўлдиргичнинг рациональ дисперслиги ўрнатилган эди, бу

дисперслик зарраларнинг геометриясини ҳисобга олган ҳолда 120-150 м<sup>2</sup>/кг ни ташкил этади. Шундан келиб чиқсан ҳолда, биз тўлдиргичнинг солиштирма юзасини ~150 м<sup>2</sup>/кг қилиб қабул қилдик.

Тўлдиргичнинг миқдорини аралаштирилган боғловчи массасига нисбатан 0 дан 40% гача ўзгартирилди. Экспериментлар  $20 \pm 2$  °C ҳароратда ва ҳавонинг 70-80% нисбий намлигида бажарилди. Экспериментлар жараёнида цемент қориши масининг нормал қуюқлиги, киришиш муддатлари,

боғловчининг пластик мустаҳкамлиги, цемент тошининг сиқилишдаги мустаҳкамлиги ва вақт бўйича кинетикаси тадқиқ қилинди. Экспериментларнинг 1 - жадвалда келтирилган натижалари тоғ жинслари тури ва улушининг цемент қориши маси ва цемент тошининг хоссаларига кўрсатадиган таъсирини келтирилган.

#### 1-жадвал


ЛСТ ва АЦФ қўмимчалари қўшилган қориши нормал қуюқлигининг

Боғловчи таркиби	Нормал қуюқлик, % да	Киришиш муддатлари, соат-мин	
		Бошланиши	тугashi
Эталонли	26,0	1-15	5-35
Цемент + ЛСТ 0,15	24,5	1-30	6-00
0,3	23,0	1-45	6-15
0,45	21,5	2-00	6-30
Цемент + АЦФ 0,05	23,0	1-35	5-45
0,1	22.5	1-50	6-20
0,15	21.0	1-80	6-35

кўрсаткичлари ва киришиш муддалари

Цемент қориши масининг сувлабчанилигига ЛСТ қўшимчаси кўпроқ ўзтаъсирини кўрсатади, униқабулқилинган улуши чегараларида қўшиш сувлабчаниликни 6-12% га АЦФ киритилганда эса 9-14 % гакамайди. Эҳтимол, каттаадсорбционфаоллик эвазига АЦФ қўшимчаси кўпроқ суюлтирувчитаъсири кўрсатиши мумкин, буни цемент тошининг пластиклигит ўғрисида гимаълумотлар ҳамтасдиқлади (1-расм).

Конус чўкиши бўйича нормал қуюқликдаги цемент тошининг пластиклиги



1 - расм.

1-Эталон


2-80%Ц+20%ЛТС билан актив бархан куми

3-80% Ц + 20 %АЦФ билан актив бархан куми

ЛСТ қўшимчасининг 0,15-0,45% да қўшилиши цемент хамирининг ёйилишини 60-100 мм га оширади. Нордан (ачитилган) қўшимчалар боғловчининг ҳосил қилган кристаллгидратлари сирти билан ўзаро таъсирашувининг кислотали-асос характеристи билан, биринчи навбатда, кальций гидроксиди билан шарт-шароитланган секинлаштирувчи таъсир кўрсатади.

0,15-0,45% ли ЛСТ қўшимчаси цемент тошини киришишининг бошланишини 15-45 минутга тезлаштириди, унинг киришиши тугашини эса 22-55 минутга оширди АЦФ 0.1% киритилганда цемент тошини киришишини бошланиши 20-50 минутга тезлаштириди, киришишни тугashi 29-61 минутга ошди. Цемент тоши мустаҳкамлиги ўзаришининг ўзига хос жиҳати қўшимча миқдори боғлиқлиги – қўшимчани 0.3% дозировкасида максимум кўрсаткич билан экспериментал характер касб этади (2-расм).

Цемент тоши мустаҳкамлигининг қўшиладиган қўшимча миқдорига боғлиқлиги



2 - расм.

1-цемент ва ЛТС

2-цемент ва АЦФ

Бу шу билан узвий боғланганки, бунда сув талабчанлик камайтирилганда цемент тоши мустаҳкамлиги, қўшимчанинг маълум бир миқдоригача ошади, ундан кейин қўшимча миқдори оширилганда ҳам сув талабчанликни камайтиришга қарамасдан мустаҳкамлик суюлтирувчи қўшимчанинг ортиқчалиги туфайли ошмайди. Бундан ташқари, маълумки, нордон табиатли қўшимчалар структура ҳосил бўлишининг коагуляцион даврини турғунлаштиради, шу билан қотаётган цемент тошида ички кучланишни пасайтиради ва унинг мустаҳкамлигининг ошишига шарт-шароит яратади. Буни, эҳтимол, тўлиқ ишонч билан ЛСТ қўшимчасига тегишли деса ҳам бўлади.

#### ФОЙДАЛАНИЛГАН АДАБИЁТЛАР:

1. Кассандрова О.И., Лебедев В.В. Обработка результатов наблюдений. - М 1990. – 68с.
2. Хигерович М.И., Байер В.Е Гидрофобно-пластифицирующие добавки для цементов, растворов и бетонов. – М.: Стройиздат, 1989.-126с.
3. Батраков В.Г. Модифицированные бетоны. - М.: Стройиздат, 2000. – С.395.
4. Дворкин Л.И., Соломатов В.И., Выровой В.Н., Чудновский С.М. Цементные бетоны с минеральными наполнителями. – Киев, 1991. – 136с
5. Saydaliyevich, U. S., Abdurashid ogli, A. S., & Qurbanboy ogli, X. J. (2021). UNDERSTANDING AND CONCEPTING BALLS IN THE SPIRIT OF MILITARY PATRIOTISM. Galaxy International Interdisciplinary Research Journal, 9(12), 924-929.
6. Ismoilovich, M. R., Saydaliyevich, U. S., & Murodjon og, B. K. (2022, May). РОЛЬ ВОЕННОЙ ПЕДАГОГИКИ И ПСИХОЛОГИИ В ВООРУЖЕННЫХ СИЛАХ. In INTERNATIONAL SCIENTIFIC RESEARCH CONFERENCE (Vol. 1, No. 4, pp. 447-452).
7. Akhmedov, A. N., & Abdurakhimov, S. A. (2018). The study of the grinding process of rushanka from the nuclei of cotton seeds of different varieties. CHEMISTRY AND CHEMICAL ENGINEERING, 2018(3), 17.
8. Saydaliyevich, U. S. (2022). Struggle of the peoples of Central Asia against the Achaemenids Tomaris, Shirak. Periodica Journal of Modern Philosophy, Social Sciences and Humanities, 6, 64-67.
9. Ogli, Y. A. B., Ogli, A. J. I., & Ogli, U. S. S. (2021). HOLY DEFENSE OF THE COUNTRY. Galaxy International Interdisciplinary Research Journal, 9(10), 544-546.
10. Tojimatovich, A. A., & Saydaliyevich, U. S. (2021). Formation Of Science as A Value and Classification of Values. Texas Journal of Multidisciplinary Studies, 3, 172-178.
11. Arabboy, Y., Sardorbek, S., & saidakbar Saydaliyevich, U. (2022). PEDAGOGICAL OPPORTUNITIES FOR DEVELOPING CREATIVITY IN

- FUTURE TEACHERS ON THE BASIS OF ACCOLOGICAL APPROACH. FORMATION OF PSYCHOLOGY AND PEDAGOGY AS INTERDISCIPLINARY SCIENCES, 1(9), 280-283.
12. Khalilovich, M. S., Saydaliyevich, U. S., & Ogli, A. O. M. (2022). EDUCATION OF YOUNG PEOPLE IN THE SPIRIT OF MILITARY AND PATRIOTISM. Galaxy International Interdisciplinary Research Journal, 10(2), 572-574.
13. Kuyoshbek, Y., Nurmukhammad, K., Arabboy, Y., Sardorbek, S., & Saydaliyevich, U. S. (2022, May). THE CONQUEST OF CENTRAL ASIA BY THE ARABS. In INTERNATIONAL SCIENTIFIC RESEARCH CONFERENCE (Vol. 1, No. 4, pp. 130-134).